

STARGARD[®] Discrete Mesh Anodes

The STARGARD[®] Discrete Mesh Anodes compliments our existing ELGARD[®] and LIDA[®] anode product line for the Cathodic protection of steel reinforced concrete structures.

It is composed of a precious metal oxide catalyst on an expanded titanium mesh substrate. The STARGARD[™] Discrete Anode is available in 150 mm, 200 mm, and 300 mm lengths that can be combined to meet specific requirements.

Dimension:

Dimensions	mm	in
Anode Diameter	19	0,75
Installation Hole Diameter	20,6	0,81
Lengths	Variabile ¹	Variabile ¹
Expanded Mesh Thickness	0,6	0,024
Diamond Dimensions	3x1,9	0,12x0,074
Strand Thickness	0,5	0,0196

(1) See Anode Performance Charts






Substrate:

Composition	Titanium, Grade 1 per ASTM B265
Coefficient of thermal expansion	8.7x10 ⁻⁵ /°K (0.0000048/in/in/°K)
Thermal conductivity at 20°C	15.6 W/m ² -°K (9.0 BTU/hr/ft ² /°F/ft)
Electrical resistivity	0.000056 ohm-cm (0.000022ohm-in)
Modulus of elasticity min.	105 Gpa (14.900.000 PSI)
Tensile strength min.	245 Mpa (35.000 PSI)
Yield strength min.	175 Mpa (25.000 PSI)
Elongation min.	24%



Stargard™ 19mm anode performance:

Maximum Current Density (CD) @ Anode	220 mA/m ²			
Mesh Length - mm (ft)	150 (0.492)	200 (0.656)	300 (0.984)	
Anode Surface Area - mm ² (ft ²)	0.0244 (0.263)	0.0326 (0.351)	0.0489 (0.526)	
Current Rating @ Max CD (mA)	5.37	7.17	10.76	
Expected design life (years)	50			
Anode Coating	Iridium Oxide, Mixed Metal Oxide			
Substrate composition	ASTM B265 Titanium Grade 1			



DE NORA INDIA LIMITED

Plot Nos. 184,185&189, Kundaim Industrial Estate, Kundaim- 403115, Goa, India.
 Ph: +91(0832) 6731100 Web: india.denora.com

© Copyright 2021 Industrie De Nora S.p.A. - All rights reserved.
 De Nora, ON circle, are trademarks or registered trademarks of Industrie De Nora S.p.A. in Europe and/or other countries. Other trademarks used herein are the registered trademarks of their respective owners.
 The information contained herein is offered for use by technically qualified personnel at their discretion and risk without warranty of any kind.

info.dni@denora.com www.denora.com

